

Dual-layer, chemical-resistant EMS gloves, offering wearers advanced barrier protection

- **Reinforced defenses:** MICROFLEX[®] LifeStar EC™ 93-868 chemical-resistant EMS gloves' dual-layer, dual-color design offers users reinforced barrier protection and chemical resistance
- **Specialized protection:** These nitrile gloves' layered design also satisfies EN 374 Type B standards for chemical splash protection
- **Sustained grip:** Textured fingertips and a non-stick/non-foaming composition help medical users and healthcare professionals maintain a strong grip in dry and wet conditions
- **Extended protection:** These medical gloves' boast an extended cuff over the wrist and lower forearm, protecting workers on the job
- **Low AQL:** These medical exam gloves' low 0.65 AQL reinforces their barrier integrity



Industries

- Chemical
- Life Sciences
- Food Processing
- Healthcare

Recommended For

- Administering drugs
- Inspection, selecting, checking parts
- Sample taking and processing
- Transferring liquids and solids

TECHNICAL DATA SHEET

Product Information	
External Glove Surface	Textured Fingers
Audit Standards	ISO 13485, ISO 9001
Product Certification	Medical Device Regulation (EU) 2017/745 Class I, Personal Protective Equipment Regulation (EU) 2016/425 Category III risks , FDA21 CFR 177-2600-US Food Contact Approved , ASTM D6319, NFPA 1999:2013,EN 455 1-4, EN 16523-1, ASTM D6977, EN ISO 21420:2020, EN ISO 374-1:2016 Type B KPT, EN ISO 374-5:2016 Virus, EN 421:2010, UKCA
Packaging Overview	100 gloves per dispenser 10 dispensers per case 1000 gloves per case
Storage Instructions	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.
Country Of Origin	Malaysia
Product Segmentation	High Risk
Antistatic	Yes EN1149
Silicone Free	No
Vulcanization Chemical Accelerators	<ul style="list-style-type: none"> Made without accelerators <p><i>Only a very small number of users may be sensitive to this ingredient(s) and hence may develop irritant and/or allergic contact reactions.</i></p>


PHYSICAL PROPERTIES

	Typical Values		Testing Method
Length (mm/inches)	≥ 280 / 11.0		ASTM D3767,EN 420
Freedom from Holes (Inspection level I)	0.65 AQL		ASTM D5151,EN 374-2
Palm Thickness (mm/mils)	0.14 / 5.5		ASTM D3767,EN 420
Finger Thickness (mm/mils)	0.21 / 8.3		ASTM D3767,EN 420
	BEFORE AGING	AFTER AGING	
Ultimate Tensile Strength (MPa)	≥ 25	≥ 25	ASTM D412 & D573
Elongation at Break (%)	≥ 700	≥ 650	ASTM D412
Force at break (N)	≥ 10	≥ 9	EN 455-2

ORDERING INFORMATION

Size	S (6.5 - 7)	M (7.5 - 8)	L (8.5 - 9)	XL (9.5 - 10)	XXL (10.5 - 11)
Product Code	93868070	93868080	93868090	93868100	93868110

Performance Standards and Regulatory Compliance



For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV
T: +32 (0) 2 528 74 00
F: +32 (0) 2 528 74 01

Asia Pacific Region

MY +603 8310 6688
apac.medical@ansell.com
CN: +86 21 38275000
infochina@ansell.com
JP: +813 5549 8151
info.medical.jp@ansell.com

North America Region

Ansell Healthcare Products LLC
T: +1 800 800 0444
F: +1 800 800 0445

Latin America & Caribbean Region

BR +55 (11) 3356-3100
latam.medical@ansell.com
MX: +52 442 296 2050
latam.medical@ansell.com
CO: +57 1 288 3247
latam.medical@ansell.com

Australia

Ansell Limited
T: +61 1800 337 041
F: +61 1800 803 578

Russia

Ansell PYC
Ten. +7 495 258 13 16

Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending; www.ansell.com/patentmarking © 2025 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

