

73-847

Neoprene Exam Glove with ERGOFORM Ergonomic Design Technology

Gloves ergonomically designed with exceptional grip

- ERGOFORM™ Technology: MICROFLEX® 73-847 gloves are designed with proprietary technology to reduce hand fatigue
- Excellent wet grip: This neoprene glove has a "grippy" textured outer finish for good grip in wet or dry environments. Certified by U.S. Ergonomics for wet performance*
- Comfortable fit and heightened sensitivity: Soft and pliable neoprene provides tactile sensitivity & comfort for longer periods
- Reduced allergy risk: Made without natural rubber proteins and powder to help protect workers from Type 1 (latex) allergies

*This product was certified by United States Ergonomics as it demonstrated exceptional wet grip performance in a variety of wet grip test conditions these included gripping tests involving soap solutions, artificial saliva, artificial blood.



Industries

• Life Sciences

Recommended For

- Plant disinfection and sanitization
- Maintaining lab furniture and equipment
- Transferring liquids and solids
- Transferring liquids
- Loading centrifuges and chromatography columns
- Assembly of parts
- Sample taking and processing
- Blending, compounding solids and liquids
- Raw material sample collection
- Damp donning



TECHNICAL DATA SHEET

	Product Information		
External Glove Surface	Textured Fingers		
Audit Standards	ISO 13485:2003		
Product Certification	ASTM D6977, Category III, EN ISO 21420:2020, EN ISO 374-1:2016 Type B KPT, EN ISO 374-5:2016 Virus, EN 421:2010, UKCA		
Packaging Overview	100 gloves per dispenser 10 dispensers per case 1000 gloves per case		
Storage Instructions	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.		
Country Of Origin	Indonesia		
Product Segmentation	Multi-Purpose		
Antistatic	No		
Silicone Free	No		
Vulcanization Chemical Accelerators	 Zinc Dibutyldithiocarbamate (ZDBC) Only a very small number of users may be sensitive to this ingredient(s) and hence may develop irritant and/or allergic contact reactions. 		

PHYSICAL PROPERTIES

	Typical	Testing Method	
Length (mm/inches)	245 / 9.6		ASTM D3767,EN 420
Freedom from Holes (Inspection level I)	1.5 AQL		ASTM D5151,EN 455-1
Palm Thickness (mm/mils)	0.10 / 3.9		ASTM D3767,EN 420
Finger Thickness (mm/mils)	0.13 / 5.1		ASTM D3767,EN 420
	BEFORE AGING	AFTER AGING	
Ultimate Tensile Strength (MPa)	≥ 18	≥ 14	ASTM D412 & D573
Elongation at Break (%)	≥ 500	≥ 400	ASTM D412
Force at break (N)	<6	<6	

ORDERING INFORMATION

Size	XS (5.5 - 6)	S (6.5 - 7)	M (7.5 - 8)	L (8.5 - 9)	XL (9.5 - 10)
Product Code	73847060	73847070	73847080	73847090	73847100

Performance Standards and Regulatory Compliance









For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region Ansell Healthcare Europe NV T: +32 (0) 2 528 74 00 F: +32 (0) 2 528 74 01

Asia Pacific Region MY +603 8310 6688 apac.medical@ansell.com CN: +86 21 38275000 infochina@ansell.com JP: +813 5549 8151 North America Region Ansell Healthcare Products LLC T: +1 800 800 0444 F: +1 800 800 0445

Latin America & Caribbean Region BR +55 (11) 3356-3100 latam.medical@ansell.com MX: +52 442 296 2050 latam.medical@ansell.com CO: +57 1 288 3247 latam.medical@ansell.com Australia
Ansell Limited
T: +61 1800 337 041
F: +61 1800 803 578

Russia Ansell PYC Ten. +7 495 258 13 16 **Technology**



Ansell, $^{\textcircled{8}}$ and $^{\textcircled{M}}$ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: www.ansell.com/patentmarking $^{\textcircled{9}}$ 2025 Ansell Limited. All Rights Reserved.

