



BioClean-D™ Coverall with Collar BDCCT

Non-sterile, disposable coverall with collar for protection against chemicals

- **Specialized protection:** The BioClean-D Coverall with Collar BDCCT is manufactured from Ansell's innovative CleanTough™ material, granting it lightweight and low-linting characteristics
- **Optimized fit:** This BioClean™ coverall is composed of a collar and protective flap for splash protection, as well as an elasticated back, cuffs, and ankles, with thumb loops to facilitate a firmer hold
- **Reduced contaminant risks:** The BioClean-D Coverall with Collar BDCCT is manufactured in accordance with ISO cleanroom standards, resulting in a cleanroom coverall that is certifiably clean and suitable



Key Features and Benefits

- **CleanTough™ material:** For a low-linting antistatic coverall
- **Elastic thumb loops:** Firm, secure hold, for everyday usability
- **Protective flap and zip with sealable cover:** Lower contamination risks

Industries

- Controlled and Critical Environments
- Production and Manufacturing
- Pharmaceutical Manufacturing
- Biotechnology Manufacturing
- Medical Device Manufacturing





BioClean-D™ Coverall with Collar BDCCT

TECHNICAL DATA SHEET

PRODUCT INFORMATION

Material	CleanTough™
Audit Standards	ISO 14001, Manufacturing QMS Audit Standards ISO 9001, PPE Regulation 2016 425 Module D, NEBB Certified Cleanrooms
Standards	ASTM F739, CE 0598, EN ISO 13688:2013, EN 1149-5:2018, EN 13934-1, EN 13935-2, EN 7854, EN 863, EN 9073-4, EN ISO 13982-1:2004 + A1:2010, EN ISO 14325, Category III, EN ISO 13982-1:2004 + A1:2010, EN 13034:2005 + A1:2009
Packaging Overview	One piece aseptically folded per sealed inner PE bag; one inner bag per sealed outer PE bag; 20 outer bags per lined carton (20 pieces). Please note: Size XXXL, XXXXL, 5XL, 6XL, & 7XL 15 pieces per carton and subject to Minimum Order Quantity and lead time.
Country Of Origin	China
Cleanroom Class	Class 10/ISO Class 4 & EU GMP Grade A/B and other sterile cleanrooms
Shelf Life	Five (5) years from date of manufacture.
Construction	Bound seams with single needle stitching

PARTICLE SHEDDING TEST RESULTS

TEST	RESULT
Particle Shedding (Helmke Drum Test)	≥ 0.5Qm (counts/min) <2000

ASTM F739-12 TEST METHOD RESULTS

DRUG	Mean Breakthrough Time (MBT), Minutes Breakthrough of the test chemical is deemed to have occurred when the permeation rate has reached 0.1 Qg/cm ² /min
CISPLATIN	>240
CARMUSTINE	<6
CYCLOPHOSAMIDE	217 (275,162,215)
DOXORUBICINHYDROCHLORIDE	>240
5-FLUOROURACIL	>240
METHOTREXATE	>240
ETOPOSIDE	>240
PACLITAXEL	<10
THIOTEPA	30 (28,30,33)

Results achieved under controlled laboratory conditions, by accredited external testing laboratory. *For Bioclean D and Bioclean 2000, the chemical permeation results relates to the fabric performance for reference only. Seams and closures may have lower breakthrough times. We recommend garments with sealed seams such as Bioclean-C to be worn over the coverall for added protection against chemotherapy drugs handling.

SIZE CHART

BDCCT-S; Size: S, Chest: 84-92cm (33"-36"), Height: 164-170cm (5'4"-5'6")
 BDCCT-M; Size: M, Chest: 92-100cm (36"-39"), Height: 170-176cm (5'6"-5'9")
 BDCCT-L; Size: L, Chest: 100-108cm (39"-42"), Height: 176-182cm (5'9"-6'0")
 BDCCT-XL; Size: XL, Chest: 108-116cm (42"-45"), Height: 182-188cm (6'0"-6'2")
 BDCCT-XXL; Size: 2XL, Chest: 116-124cm (45"-48"), Height: 188-194cm (6'2"-6'4")
 BDCCT-XXXL; Size: 3XL, Chest: 124-132cm (48"-51"), Height: 194-200cm (6'4"-6'6")
 BDCCT-XXXXL; Size: 4XL, Chest: 132-140cm (51"-54"), Height: 200-206cm (6'6"-6'8")
 BDCCT-5XL; Size: 5XL, Chest: 140-148cm (54"-57"), Height: 206-212cm (6'8"-6'10")
 BDCCT-6XL; Size: 6XL, Chest: 148-156cm (58"-61"), Height: 212-218cm (6'10"-6'12")
 BDCCT-7XL; Size: 7XL, Chest: 156-164cm (61"-64"), Height: 218-224cm (7'1"-7'3")



BioClean-D™ Coverall with Collar BDCCT

MATERIAL PERFORMANCE TEST RESULTS

TEST	RESULT	PERFORMANCE CLASS	PERFORMANCE STANDARD
Abrasion Resistance	>10 cycles	1	EN 12947-2
Flex Cracking Resistance	>50,000 cycles	6	EN ISO 7854
Puncture Resistance	>5 N	1	ISO 13996
Trapezoidal Tear Resistance Cross Direction (CD)	>10 N	1	EN ISO 9073-4
Trapezoidal Tear Resistance Machine Direction (MD)	>10 N	1	EN ISO 9073-4
Tensile Strength Cross Direction (CD)	>30 N	1	EN ISO 13934-1
Tensile Strength Machine Direction (MD)	>30 N	1	EN ISO 13934-1
Repellence to Liquids - 30% H ₂ SO ₄	>90%	3	ISO 6530
Repellence to Liquids - 10% NaOH	>90%	3	ISO 6530
Repellence to Liquids - O-Xylene	>90%	3	ISO 6530
Repellence to Liquids - Butan-1-ol	>90%	3	ISO 6530
Penetration by Liquids - 30% H ₂ SO ₄	<1%	3	ISO 6530
Penetration by Liquids - 10% NaOH	<1%	3	ISO 6530
Penetration by Liquids - O-Xylene	<1%	3	ISO 6530
Penetration by Liquids - Butan-1-ol	<1%	3	ISO 6530
Inward leakage of aerosols of fine particles ¹	PASS	N/A	EN ISO 13982-2
Resistance to penetration by spray (Spray Test) ¹	PASS	N/A	EN ISO 17491-4
Seam Strength ²	>50 N	2	ISO 13935-2
Electrostatic Charge Half Decay Time, t ₅₀ (secs)	PASS	N/A	EN1149-3

1. All interfaces with additional PPE were taped during testing, as required by the standards.
 2. Seam not destroyed., 3. The material is static dissipative. Tested in accordance with EN1149-5

ORDERING INFORMATION

	SIZE	S, M, L, XL, 2XL	BDCCT-3XL, BDCCT-4XL, BDCCT-5XL, BDCCT-6XL, BDCCT-7XL
BDCCT	REORDER NO.	BDCCT-S, BDCCT-M, BDCCT-L, BDCCT-XL, BDCCT-2XL	BDCCT-3XL, BDCCT-4XL, BDCCT-5XL, BDCCT-6XL, BDCCT-7XL

For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV
 T: +32 (0) 2 528 74 00
 F: +32 (0) 2 528 74 01

Asia Pacific Region

Ansell Global Trading Center
 T: +603 8310 6688
 F: +603 8310 6699

North America Region

Ansell Healthcare Products LLC
 US T: +1 800 800 0444
 US F: +1 800 800 0445
 CA T: +1-800-363-8340

Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.
 T: +52 442 248 1544 / 248 3133

Australia

Ansell Limited
 T: +61 1800 337 041
 F: +61 1800 803 578

UK

Ansell Nitritex
 T: +44 1638 663338
 F: +44 1638 668890

Performance Standards and Regulatory Compliance



Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: www.ansell.com/patentmarking © 2024 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

Please see product validation pack or contact Ansell customer service for specific data on use of garments with cytotoxic drugs. Garments used for protection against such drugs must be selected specifically for the type of chemicals used.

