

**GGL20NIT59** Validated Sterile Nitrile RABS / Isolator Gloves

# Validated, sterile nitrile RABS/isolator gloves

Port size: 203mm/8"

- Advanced defenses: These nitrile sterile gloves are tested against ASTM D6978-05 standards, for safe chemotherapy drug handling and resistance to common chemicals
- Enhanced safety: These nitrile isolator/RABS gloves are 100% water leak tested, for reliable personal and product protection
- Optimized cleanliness: These gloves are washed and packed in an ISO Class 4 cleanroom, ensuring low particulate levels
- Improved fit: BioClean™ Nitrile Sterile RABS/Isolator Gloves GGL20NIT59 are designed to lessen hand fatigue
- Specialized protection: These nitrile isolator/RABS gloves are also resistant to vaporized hydrogen peroxide (VHP), isopropyl alcohol (IPA) and common disinfectants

## **KEY FEATURES & BENEFITS**

- ASTM D6978-05 compliance: Cytotoxic drug and chemical resistance
- 100% water leak tested: Assured glove integrity
- SAL (Sterility Assurance Level) of 10-6: Ultra-clean sterile hand protection

#### Industries

- Pharmaceutical Manufacturing
- Laboratory Research and Development
- Raw Material and Preparation
- Biotechnology Manufacturing
- Sterile Processing Department
  Semiconductor manufacturing

Ansell





## **TECHNICAL DATA SHEET**

Product Reference	GGL20NIT59
Material	Nitrile
Color	White
Shape	Ambidextrous
External Glove Surface	Smooth
Cuff Style	Beaded
Audit Standards	ISO 14001, Manufacturing QMS Audit Standards ISO 9001, PPE Regulation 2016 425 Module D, NEBB Certified Cleanrooms
Packaging Overview	One piece per sealed inner PE bag; one inner bag per sealed second inner PE bag; one second inner bag per sealed outer PE bag; 20 outer bags per lined inner white Correx polyethylene box (20 pieces).
Storage Instructions	Store in a dry, cool place (<40°C) away from direct sunlight and fluorescent light.
Country Of Origin	Malaysia
Available Sizes	9.75
Temperature Range	From -10°C to 120°C
Sterilization Method	GAMMA irradiation (25 kGy)
Cleanroom Class	Class 10/ISO 4 & EU GMP Grade A
Shelf Life	Three (3) years from date of manufacture.
Tested For Use With Chemotherapy Drugs	Yes, in accordance with ASTM D6978 (Not listed in the US FDA 510k)
Protein Level	N/A: contains no natural rubber latex
Standards	ASTM D6978, CE 0493, EC 1935/2004, ISO 11137-1:2006, EN 420:2003 + A1:2009, EN 421:2010, EN ISO 374-5:2016, EN ISO 374-1:2016, EN 388:2016, EN 455 Part 2, Category III



GGL20NIT59 Validated Sterile Nitrile RABS / Isolator Gloves

## **PHYSICAL PROPERTIES**

	Typical Values	Testing Method
Sizes	9.75	
Typical Length (mm/in)	840/33	EN ISO 21420
Palm Width (mm/in)	129/5.1	EN ISO 21420
Port Size	8"	
Target Single Wall Palm Thickness (mm/mil)	0.50 /20	EN 455-2
Target Single Wall Finger Thickness (mm/mil)	0.60/24	EN 455-2
Target Single Wall Cuff Thickness (mm/mil)	0.50/20	EN 455-2

## **PROTECTION AGAINST MECHANICAL RISKS, EN 388:2016+A1:2018**

Risk	Performance level
Abrasion Resistance	Level 4
Blade Cut Resistance	Level 1
Tear Resistance	Level O
Puncture Resistance	Level 2

#### **ORDERING INFORMATION**

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV T: +32 (0) 2 528 74 00 F: +32 (0) 2 528 74 01

Ansell Global Trading Center T: +603 8310 6688 F: +603 8310 6699

Asia Pacific Region

	PORT SIZE	8"/203mm
	SIZE	9.75
GGL20NIT59	REORDER NO.	GGL20NIT59

#### Technology



#### **Performance Standards and Regulatory Compliance**



For additional information visit us at www.ansell.com, or call us at Australia Ansell Limited T: +61 1800 337 041 F: +61 1800 803 578

UΚ Ansell Nitritex T: +44 1638 663338 F: +44 1638 668890

Ansell, <sup>®</sup> and <sup>™</sup> are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: www.ansell.com/patentmarking © 2024 Ansell Limited. All Rights Reserved.

Ansell Healthcare Products LLC US T: +1 800 800 0444 US F: +1 800 800 0445 CA T: +1-800-363-8340

Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V. T: +52 442 248 1544 / 248 3133

North America Region

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

