

White nitrile medical exam glove with HYDRASOFT™ Skin Moisturizing Technology

- **HYDRASOFT™ Skin Moisturizing Technology:** Unique inner coating is proven to help skin retain 2x more moisture* than gloves without HYDRASOFT™ Technology, preventing dryness and discomfort
- **Comfortable fit:** The soft, nitrile formulation provides a comfortable fit and feel
- **Heightened tactility:** The lightweight nitrile construction provides extra comfort and tactility while working

*based on internal testing (data on file)



NOW FEATURING
HYDRASOFT™
Skin Moisturizing Technology

Industries

- Dental
- Healthcare
- Life Sciences

Recommended For

- Sample taking and processing
- Protection from Type I latex allergy in HCW's or patients
- Standard patient examinations
- Enhanced tactile sensitivity and dexterity, especially for delicate procedures
- Oral examinations
- Laboratory analysis
- Testing
- Helping protect skin from drying or cracking
- Pharmaceutical manufacturing
- General dentistry

TECHNICAL DATA SHEET

Product Information	
External Glove Surface	Textured Fingers
Audit Standards	ISO 13485, ISO 9001
Product Certification	Medical Device Regulation (EU) 2017/745 Class I
Packaging Overview	100 gloves per dispenser 10 dispensers per case 1000 gloves per case
Storage Instructions	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.
Country Of Origin	Indonesia
Product Segmentation	High Touch
Antistatic	Not Tested
Vulcanization Chemical Accelerators	<ul style="list-style-type: none"> Zinc Dibutyldithiocarbamate (ZDBC) Zinc Diethyldithiocarbamate (ZDEC) <p><i>Only a very small number of users may be sensitive to this ingredient(s) and hence may develop irritant and/or allergic contact reactions.</i></p>

PHYSICAL PROPERTIES

	Typical Values		Testing Method
Length (mm/inches)	245 / 9.6		ASTM D3767,EN 420
Freedom from Holes (Inspection level I)	1.5 AQL		ASTM D5151,EN 455-1
Palm Thickness (mm/mils)	0.07 / 2.8		ASTM D3767,EN 420
Finger Thickness (mm/mils)	0.12 / 4.7		ASTM D3767,EN 420
	BEFORE AGING	AFTER AGING	
Ultimate Tensile Strength (MPa)	≥ 14	≥ 14	ASTM D412 & D573
Elongation at Break (%)	≥ 500	≥ 400	ASTM D412
Force at break (N)	≥ 6N	≥ 6	

ORDERING INFORMATION

Size	XS (5.5 - 6)	S (6.5 - 7)	M (7.5 - 8)	L (8.5 - 9)	XL (9.5 - 10)
Product Code	TQ-601-XS	TQ-601-S	TQ-601-M	TQ-601-L	TQ-601-XL

Performance Standards and Regulatory Compliance



For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV
T: +32 (0) 2 528 74 00
F: +32 (0) 2 528 74 01

Asia Pacific Region

MY +603 8310 6688
apac.medical@ansell.com
CN: +86 21 38275000
infochina@ansell.com
JP: +813 5549 8151
info.medical.jp@ansell.com

North America Region

Ansell Healthcare Products LLC
T: +1 800 800 0444
F: +1 800 800 0445

Latin America & Caribbean Region

BR +55 (11) 3356-3100
latam.medical@ansell.com
MX: +52 442 296 2050
latam.medical@ansell.com
CO: +57 1 288 3247
latam.medical@ansell.com

Australia

Ansell Limited
T: +61 1800 337 041
F: +61 1800 803 578

Russia

Ansell PYC
Ten. +7 495 258 13 16

Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending; www.ansell.com/patentmarking © 2024 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

