



BioClean-C™ Sleeve Covers - Sterile S-BCSC

Sterile cleanroom sleeve covers for protection against chemotherapy drugs

- **Optimized protection:** BioClean™ chemotherapy-protective sleeve covers are specially developed to protect against a range of chemotherapy drugs, with ultrasonically bonded seams and protective tape, for added security
- **Guaranteed cleanliness:** These chemotherapy-protective sleeves are constructed from sterile CleanTough™ material that is lightweight and low-linting
- **Assured barrier protection:** BioClean-C™ chemotherapy-protective sleeve covers have been tested against ASTM F739-12 permeation standards
- **Maximized practicality:** These one-size-fits-all sterile sleeve covers are tailored for quick and simple donning
- **Reduced contamination risks:** They are specially packaged to eliminate cross contamination and sterilized using gamma irradiation to yield a minimum SAL of 10⁻⁶



Key Features and Benefits

- **Ultrasonically bonded seam:** For sleeve covers that deliver a secure fit
- **Lightweight, low-linting CleanTough™ fabric:** Comfort and durability
- **ASTM F739-12 compliance:** For assured permeation protection

Industries

- Controlled and Critical Environments
- Production and Manufacturing
- Laboratory and Research





BioClean-C™ Sleeve Covers - Sterile S-BCSC

TECHNICAL DATA SHEET

PRODUCT INFORMATION

Material	CleanTough™
Audit Standards	Manufacturing QMS Audit Standards ISO 9001, PPE Regulation 2016 425 Module D
Standards	ASTM F739, CE 0598, EN 13935-2, EN ISO 14325, EN 14605:2005 + A1:2009, EN ISO 13688:2013+A1:2021, Partial Body Protection Only, Category III, EN 13034:2005 + A1:2009
Storage	Store in a dry cool place 40°C away from direct sunlight and fluorescent light.
Country Of Origin	China
Sterilization Method	GAMMA irradiation (25 kGy)
Sterilization Minimum Dose	25kGy
Sterility Assurance Level	10 ⁻⁶
Cleanroom Class	Class 10/ISO 4 & EU GMP Grade A
Shelf Life	Three (3) years from date of manufacture.
Construction	Ultrasonically bonded seams covered with protective tape
Characteristics	Low particulating

PARTICLE SHEDDING TEST RESULTS

TEST	RESULT
Particle Shedding (Helmke Drum Test)	≥ 0.5Qm (counts/min) <1700

ASTM F739-12 TEST METHOD RESULTS

DRUG	Mean Breakthrough Time (MBT), Minutes Breakthrough of the test chemical is deemed to have occurred when the permeation rate has reached 0.1 Qg/cm ² /min
CISPLATIN	>480
CARMUSTINE	>480
CYCLOPHOSHAMIDE	>480
DOXORUBICINHYDROCHLORIDE	>480
5-FLUOROURACIL	>480
METHOTREXATE	>480
ETOPOSIDE	>480
PACLITAXEL	>480
THIOTEPA	>456

Results achieved under controlled laboratory conditions, by accredited external testing laboratory. *For Bioclean D and Bioclean 2000, the chemical permeation results relates to the fabric performance for reference only. Seams and closures may have lower breakthrough times. We recommend garments with sealed seams such as Bioclean-C to be worn over the coverall for added protection against chemotherapy drugs handling.

SIZE CHART

S-BCSC; Size: Universal



BioClean-C™ Sleeve Covers - Sterile S-BCSC

MATERIAL PERFORMANCE TEST RESULTS

TEST	RESULT	PERFORMANCE CLASS	PERFORMANCE STANDARD
Abrasion Resistance	>10 cycles	1	EN 12947-2
Puncture Resistance	>5 N	1	ISO 13996
Trapezoidal Tear Resistance Cross Direction (CD)	>10 N	1	EN ISO 9073-4
Trapezoidal Tear Resistance Machine Direction (MD)	>10 N	1	EN ISO 9073-4
Tensile Strength Cross Direction (CD)	>30 N	1	EN ISO 13934-1
Tensile Strength Machine Direction (MD)	>30 N	1	EN ISO 13934-1
Repellence to Liquids - 30% H ₂ SO ₄	>90%	3	ISO 6530
Repellence to Liquids - 10% NaOH	>90%	3	ISO 6530
Repellence to Liquids - O-Xylene	>90%	3	ISO 6530
Repellence to Liquids - Butan-1-ol	>90%	3	ISO 6530
Penetration by Liquids - 30% H ₂ SO ₄	<1%	3	ISO 6530
Penetration by Liquids - 10% NaOH	<1%	3	ISO 6530
Penetration by Liquids - O-Xylene	<1%	3	ISO 6530
Penetration by Liquids - Butan-1-ol	<1%	3	ISO 6530
Seam Strength ¹	>50 N	2	ISO 13935-2

For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV
T: +32 (0) 2 528 74 00
F: +32 (0) 2 528 74 01

Asia Pacific Region

Ansell Global Trading Center
T: +603 8310 6688
F: +603 8310 6699

North America Region

Ansell Healthcare Products LLC
US T: +1 800 800 0444
US F: +1 800 800 0445
CA T: +1-800-363-8340

Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.
T: +52 442 248 1544 / 248 3133

Australia

Ansell Limited
T: +61 1800 337 041
F: +61 1800 803 578

UK

Ansell Nitritex
T: +44 1638 663338
F: +44 1638 668890

Performance Standards and Regulatory Compliance

CE 0598



Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: www.ansell.com/patentmarking © 2024 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

Please see product validation pack or contact Ansell customer service for specific data on use of garments with cytotoxic drugs. Garments used for protection against such drugs must be selected specifically for the type of chemicals used.

