

## Sterile disposable coveralls with hood and overboots, combining protection and comfort

- **Enhanced protection:** The BioClean-D™ Sterile Kit S-BAKCT's three-piece design comprises a hood, coverall and overboots, providing head-to-toe personal protection
- **Improved fit and practicality:** Tie fastenings and thumb loops enable wearers to adjust the fit to suit their needs and easily maintain a secure hold
- **Elevated comfort:** Designed with comfort in mind, this sterile kit also features an elasticated back, cuffs and ankles, as well as a convenient front zip with a protective flap
- **Sterility assurance:** The kit is sterilized by gamma irradiation, with a sterility assurance level (SAL) of 10<sup>-6</sup>



### Key Features and Benefits

- **Three-piece design:** Head-to-toe personal protection
- **Lightweight low-linting material:** Lower contamination risks
- **Tie fastenings and slip-resistant sole:** A secure fit and safer use

### Industries

- Controlled and Critical Environments
- Laboratory and Research
- Production and Manufacturing





# BioClean-D™ Sterile Kit S-BAKCT

## TECHNICAL DATA SHEET

### PRODUCT INFORMATION

<b>Material</b>	CleanTough™
<b>Color</b>	White
<b>Audit Standards</b>	ISO 9001:2015
<b>Standards</b>	ASTM F739, EN 1149-5:2008, EN 13935-2, EN ISO 13688:2013, Category III, EN ISO 13982-1:2004 + A1:2010, EN 13034:2005 + A1:2009
<b>Packaging Overview</b>	One hood, one coverall with collar, and one pair of overboots per sealed inner bag; one inner bag per sealed outer PE bag; 15 outer bags (kits) per carton
<b>Storage</b>	Store in a dry cool place 40°C away from direct sunlight and fluorescent light.
<b>Country Of Origin</b>	Malaysia
<b>Sterilization Method</b>	GAMMA irradiation (25 kGy)
<b>Sterilization Minimum Dose</b>	25kGy
<b>Sterility Assurance Level</b>	10 <sup>-6</sup>
<b>Cleanroom Class</b>	Class 10/ISO 4 & EU GMP Grade A
<b>Shelf Life</b>	Three (3) years from date of manufacture.
<b>Construction</b>	Hood Elasticated face opening, reinforced edges Coverall Zip front with flap cover. Thumb loops on wrist Elasticated back, cuffs and ankles Overboots Elasticated top with secure ties at top and slip-resistant soles
<b>Characteristics</b>	*NOTE: BioClean CleanTough material is static dissipative and, with a charge half decay time of 0.07 sec, and so are ideal for use in a static-safe environment.

### PARTICLE SHEDDING TEST RESULTS

TEST	RESULT
Particle Shedding (Helmke Drum Test)	≥ 0.5Qm (counts/min) <2000

### ASTM F739-12 TEST METHOD RESULTS

DRUG	Mean Breakthrough Time (MBT), Minutes
CISPLATIN	>240
CARMUSTINE	<6
CYCLOPHOSAMIDE	217 (275, 162, 215)
DOXORUBICINHYDROCHLORIDE	>240
5-FLUOROURACIL	>240
METHOTREXATE	>240
ETOPOSIDE	>240
PACLITAXEL	<10
THIOTEPA	30 (28, 30, 33)

Results achieved under controlled laboratory conditions, by accredited external testing laboratory. \*For Bioclean D and Bioclean 2000, the chemical permeation results relates to the fabric performance for reference only. Seams and closures may have lower breakthrough times. We recommend garments with sealed seams such as Bioclean-C to be worn over the coverall for added protection against chemotherapy drugs handling.

### SIZE CHART

S-BAKCT-S; Size: S, Chest: 84-92cm (33"-36"), Height: 164-170cm (5'4"-5'6")  
 S-BAKCT-M; Size: M, Chest: 92-100cm (36"-39"), Height: 170-176cm (5'6"-5'9")  
 S-BAKCT-L; Size: L, Chest: 100-108cm (39"-42"), Height: 176-182cm (5'9"-6'0")  
 S-BAKCT-XL; Size: XL, Chest: 108-116cm (42"-45"), Height: 182-188cm (6'0"-6'2")  
 S-BAKCT-2XL; Size: 2XL, Chest: 116-124cm (45"-48"), Height: 188-194cm (6'2"-6'4")



# BioClean-D™ Sterile Kit S-BAKCT

## MATERIAL PERFORMANCE TEST RESULTS

TEST	RESULT	PERFORMANCE CLASS	PERFORMANCE STANDARD
Abrasion Resistance	>10 cycles	1	EN 12947-2
Flex Cracking Resistance	>50,000 cycles	6	EN ISO 7854
Puncture Resistance	>5 N	1	ISO 13996
Trapezoidal Tear Resistance Cross Direction (CD)	>10 N	1	EN ISO 9073-4
Trapezoidal Tear Resistance Machine Direction (MD)	>10 N	1	EN ISO 9073-4
Tensile Strength Cross Direction (CD)	>30 N	1	EN ISO 13934-1
Tensile Strength Machine Direction (MD)	>30 N	1	EN ISO 13934-1
Repellence to Liquids - 30% H <sub>2</sub> SO <sub>4</sub>	>90%	3	ISO 6530
Repellence to Liquids - 10% NaOH	>90%	3	ISO 6530
Repellence to Liquids - O-Xylene	>90%	3	ISO 6530
Repellence to Liquids - Butan-1-ol	>90%	3	ISO 6530
Penetration by Liquids - 30% H <sub>2</sub> SO <sub>4</sub>	<1%	3	ISO 6530
Penetration by Liquids - 10% NaOH	<1%	3	ISO 6530
Penetration by Liquids - O-Xylene	<1%	3	ISO 6530
Penetration by Liquids - Butan-1-ol	<1%	3	ISO 6530
Inward leakage of aerosols of fine particles <sup>1</sup>	PASS	N/A	EN ISO 13982-2
Resistance to penetration by spray (Spray Test) <sup>1</sup>	PASS	N/A	EN ISO 17491-4
Seam Strength <sup>2</sup>	>50 N	2	ISO 13935-2
Electrostatic Charge Half Decay Time, t <sub>50</sub> (secs)	PASS	N/A	EN1149-3

1. All interfaces with additional PPE were taped during testing, as required by the standards.  
 2. Seam not destroyed., 3. The material is static dissipative. Tested in accordance with EN1149-5

## ORDERING INFORMATION

	SIZE	BioClean-D Sterile Anti-Static Kit
S-BAKCT	REORDER NO.	S, M, L, XL, 2XL

For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at

### Europe, Middle East & Africa Region

Ansell Healthcare Europe NV  
 T: +32 (0) 2 528 74 00  
 F: +32 (0) 2 528 74 01

### Asia Pacific Region

Ansell Global Trading Center  
 T: +603 8310 6688  
 F: +603 8310 6699

### North America Region

Ansell Healthcare Products LLC  
 US T: +1 800 800 0444  
 US F: +1 800 800 0445  
 CA T: +1-800-363-8340

### Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.  
 T: +52 442 248 1544 / 248 3133

### Australia

Ansell Limited  
 T: +61 1800 337 041  
 F: +61 1800 803 578

### UK

Ansell Nitritex  
 T: +44 1638 663338  
 F: +44 1638 668890

## Performance Standards and Regulatory Compliance



Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: [www.ansell.com/patentmarking](http://www.ansell.com/patentmarking) © 2024 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

Please see product validation pack or contact Ansell customer service for specific data on use of garments with cytotoxic drugs. Garments used for protection against such drugs must be selected specifically for the type of chemicals used.

