

83-500

Sterile Disposable Polyisoprene Cleanroom Glove

Sterile polyisoprene gloves, designed for Class 100 (ISO 5)/Grade A cleanroom environments

- Elevated comfort: Ideal for double gloving, TouchNTuff® 83-500 polyisoprene cleanroom gloves' ultrasoft polyisoprene offers "second skin"like comfort and minimizes hand fatigue with prolonged wear
- Reduced allergy risks: They contain no latex proteins, meaning they do not pose any threat related to Type I latex allergies and sensitivities
- Sterility assurance: These disposable gloves are sterilized by gamma irradiation, with a sterility assurance level (SAL) of 10-6



KEY FEATURES & BENEFITS

- Ultra-soft polyisoprene: "Second skin" comfort and feel
- Latex-free design: Latex Type I allergy risks eliminated
- Gamma sterilization: A sterility assurance level (SAL) of 10-6

Industries

- Laboratory Maintenance & Clean-Up
- Pharmaceutical Manufacturing
- Biotechnology Manufacturing
- Medical Device Manufacturing
- Laboratory Research and Development
- Preparation of Materials
- Production & Processing
- Lab and R&D
- Controlled and Critical Environments
- Production and Manufacturing

Recommended For

- Maintaining lab furniture and equipment
- Spill or leakage cleanup
- Transferring liquids and solids
- Packaging and labeling
- Clean room cleaning and preparing
- Sample taking and processing
- Administering drugs
- Transferring liquids and solids between vessels and tanks and process equipment







83-500

Sterile Disposable Polyisoprene Cleanroom Glove

TECHNICAL DATA SHEET

| | Product Information | | | | | | |
|---|--|--|--|--|--|--|--|
| Material | PI (Polyisoprene) | | | | | | |
| Color | White | | | | | | |
| Shape | Anatomic with Curved Fingers | | | | | | |
| Cuff | Beaded with SUREFIT™ Technology | | | | | | |
| Manufacturing/QMS Audit Standards | ISO 13485, ISO 9001:2015, Manufacturing QMS Audit Standards ISO 9001, PPE Regulation 2016 425 Module D | | | | | | |
| Regulatory/Standard Compliance | AS/NZS 4179, ASTM D3577, ASTM D7160, CE 0493, EN 556-1:2001, EN ISO 21420:2020, EN ISO 374-1:2016 Type B (KPT), EN ISO 374-5:2016, EN 421:2010, Please consult the IFU, ISO 10282, ISO 11193, Category III, UKCA | | | | | | |
| | 1 pair per inner polybag; 10 pairs per outer polybag; 5 polybags per master polybags; 4 master polybags per carton; 200 pairs per carton | | | | | | |
| Packaging | More sustainable packaging: These sterile gloves are packed in recyclable plastic packaging* and delivered in recycled cardboard shipper cases. | | | | | | |
| | *Inner wrap, pouch, bag and liner are made from polyethylene (PE) based film. Always check your local recyclable status as these materials may not be considered suitable for recycling in your location. | | | | | | |
| Storage | Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition. | | | | | | |
| Country of Origin | Sri Lanka | | | | | | |
| Available sizes | 5.5, 6, 6.5, 7, 7.5, 8, 8.5, 9 | | | | | | |
| Powder Content | Powder-Free | | | | | | |
| External Glove Surface | Smooth | | | | | | |
| Internal Glove Surface | Polymer Coated with DERMASHIELD™ Technology | | | | | | |
| Sterilization Method | GAMMA irradiation (25 kGy) | | | | | | |
| Cleanroom Class | Class 100/ISO Class 5 & EU GMP Grade A/B and other sterile cleanrooms | | | | | | |
| Shelf Life | 5 Years | | | | | | |
| Tested for use with Chemotherapy Drugs | Yes | | | | | | |
| Protein Level | N/A: contains no natural rubber latex | | | | | | |
| Anti-static | No | | | | | | |





83-500

Sterile Disposable Polyisoprene Cleanroom Glove

| Physical Properties | | Testing Method |
|--|-------------|---------------------|
| Typical Length (mm/in) | 300 / 12 | EN 420/ASTM D3767 |
| Freedom from Holes | 0.65 AQL | EN 455-1/ASTM D3577 |
| Typical Particle Count ≥0.5µm (counts / cm²) | ≤ 2500 | IEST-RP-CC005.4 |
| Target Single Wall Palm Thickness (mm/mil) | 0.21 / 8.26 | EN 420/ASTM D3767 |
| Target Single Wall Finger Thickness (mm/mil) | 0.23 / 9.05 | EN 420/ASTM D3767 |
| Target Single Wall Cuff Thickness (mm/mil) | 0.17 / 6.69 | EN 420/ASTM D3767 |
| Ultimate tensile strength (MPa) Before Aging | ≥17 | ASTM D412-06a |
| Ultimate tensile strength (MPa) During Aging | ≥12 | ASTM D412-06a |
| Force at Break (N) Before Aging | 9 | EN 455-2 |
| Force at Break (N) During Aging | 9 | EN 455-2 |

ORDERING INFORMATION

| SIZE | 5.5 | 6 | 6.5 | 7 | 7.5 | 8 | 8.5 | 9 |
|----------------|----------|----------|----------|----------|----------|----------|----------|----------|
| REORDER NO. | 83500055 | 83500060 | 83500065 | 83500070 | 83500075 | 83500080 | 83500085 | 83500090 |

PERFORMANCE STANDARDS AND REGULATORY COMPLIANCE













For additional information visit us at www.ansell.com, or call us at $\ensuremath{\mathsf{a}}$

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV T: +32 (0) 2 528 74 00 F: +32 (0) 2 528 74 01

Asia Pacific Region

Ansell Global Trading Center T: +603 8310 6688 F: +603 8310 6699

North America Region

Ansell Healthcare Products LLC US T: +1 800 800 0444 US F: +1 800 800 0445 CA T: +1-800-363-8340

Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V. T: +52 442 248 1544 / 248 3133

Australia

Ansell Limited T: +61 1800 337 041 F: +61 1800 803 578

UK

Ansell Nitritex T: +44 1638 663338 F: +44 1638 668890

Technology





Skin-friendly, non-se PI Technology

Cuff Roll-down Technology

Ansell, $^{\textcircled{8}}$ and $^{\textcircled{1}}$ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: www.ansell.com/patentmarking $^{\textcircled{6}}$ 2025 Ansell Limited. All Rights Reserved.

