

Latex exam gloves with exceptional fit and feel for extended wear

- **Secure grip:** MICROFLEX[®] 63-854 disposable latex gloves are fully textured for a secure grip, and in both wet or dry environments
- **Tactile sensitivity:** Excellent tactile sensitivity ensures precise handling of sensitive or delicate items, such as laboratory instruments
- **Comfortable and elastic fit:** Superior elasticity means gloves move with you for greater comfort
- **Outstanding quality:** Exceeds standards for tensile strength, elasticity/elongation and other quality standards for average latex gloves



*CAUTION: This product contains natural rubber latex, which may cause allergic reactions

Industries

- Food Processing
- Life Sciences
- Healthcare

Recommended For

- Equipment, maintenance and repair
- All food processing, applications that have food contact
- Sample taking and processing
- Extra comfort during long, sustained procedures

TECHNICAL DATA SHEET

| Product Information | |
|------------------------|----------------------------------------------------------------------------------------------------------------------------|
| External Glove Surface | Fully Textured |
| Audit Standards | ISO 13485 |
| Product Certification | Medical Device Regulation (EU) 2017/745 Class I, Personal Protective Equipment Regulation (EU) 2016/425 Category III risks |
| Packaging Overview | |
| Storage Instructions | Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition. |
| Country Of Origin | Malaysia |
| Antistatic | Not Tested |
| Silicone Free | Yes |

PHYSICAL PROPERTIES

| | Typical Values | | Testing Method |
|-----------------------------------------|----------------|-------------|----------------------|
| Length (mm/inches) | 245 / 9.6 | | ASTM D3767, EN 420 |
| Freedom from Holes (Inspection level I) | 1.5 AQL | | ASTM D5151, EN 455-1 |
| Palm Thickness (mm/mils) | 0.13 / 5.1 | | ASTM D3767, EN 420 |
| Finger Thickness (mm/mils) | 0.16 / 6.3 | | ASTM D3767, EN 420 |
| | BEFORE AGING | AFTER AGING | |
| Ultimate Tensile Strength (MPa) | 22 | 20 | ASTM D412 & D573 |
| Elongation at Break (%) | ≥ 700 | ≥ 600 | ASTM D412 |
| Force at break (N) | 9 | 6 | EN 455-2 |

ORDERING INFORMATION

| Size | XS (5.5 - 6) | S (6.5 - 7) | M (7.5 - 8) | L (8.5 - 9) | XL (9.5 - 10) |
|--------------|--------------|-------------|-------------|-------------|---------------|
| Product Code | 63854060 | 63854070 | 63854080 | 63854090 | 63854100 |

Performance Standards and Regulatory Compliance



For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region
 Ansell Healthcare Europe NV
 T: +32 (0) 2 528 74 00
 F: +32 (0) 2 528 74 01

Asia Pacific Region
 MY +603 8310 6688
 apac.medical@ansell.com
 CN: +86 21 38275000
 infochina@ansell.com
 JP: +813 5549 8151
 info.medical.jp@ansell.com

North America Region
 Ansell Healthcare Products LLC
 T: +1 800 800 0444
 F: +1 800 800 0445

Latin America & Caribbean Region
 BR +55 (11) 3356-3100
 latam.medical@ansell.com
 MX +52 442 296 2050
 latam.medical@ansell.com
 CO: +57 1 288 3247
 latam.medical@ansell.com

Australia
 Ansell Limited
 T: +61 1800 337 041
 F: +61 1800 803 578

Russia
 Ansell PYC
 Ten. +7 495 258 13 16

Ansell[®] and [™] are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: www.ansell.com/patentmarking © 2024 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

