

## Non-sterile long-length protective hood, offering comprehensive personal protection

- **Added protection:** The BioClean-D™ Hood BDHD-L non-sterile protective hood's extended length ensures greater coverage when worn with a coverall
- **Reduced contamination risks:** Due to its lightweight, low-linting material, contamination risks is minimized
- **Electrostatic dissipative properties:** The material is antistatic coated to prevent static buildup, enabling a controlled dissipation of static electricity

### Key Features and Benefits

- **Extended length:** For greater protective coverage
- **Lightweight low-linting material:** Lower contamination risks
- **ESD properties:** Minimal risk of electrostatic damage or interference



### Industries

- Controlled and Critical Environments
- Production and Manufacturing
- Pharmaceutical Manufacturing
- Biotechnology Manufacturing
- Medical Device Manufacturing





# BioClean-D™ Hood BDHD-L

## TECHNICAL DATA SHEET

### PRODUCT INFORMATION

<b>Material</b>	CleanTough™
<b>Audit Standards</b>	Manufacturing QMS Audit Standards ISO 9001, PPE Regulation 2016 425 Module D
<b>Standards</b>	ASTM F739, Partial Body Protection Only, CE 0598, EN 1149-5:2008, EN 1149-5:2018, EN 13934-1, EN 13935-2, EN 6530, EN 7854, EN 863, EN 9073-4, EN ISO 13688:2013+A1:2021, EN ISO 14325, Category III, EN 13034:2005 + A1:2009
<b>Packaging Overview</b>	20 pieces per sealed inner PE bag; one inner bag per sealed outer PE bag; six outer bags per lined carton (120 pieces)
<b>Storage</b>	Store in a dry cool place 40°C away from direct sunlight and fluorescent light.
<b>Country Of Origin</b>	China
<b>Cleanroom Class</b>	Class 10/ISO 4
<b>Shelf Life</b>	Five (5) years from date of manufacture.
<b>Construction</b>	Bound seams with single needle stitching
<b>Characteristics</b>	*NOTE: BioClean CleanTough material is static dissipative and, with a charge half decay time of 0.07 sec, and so are ideal for use in a static-safe environment.

### PARTICLE SHEDDING TEST RESULTS

TEST	RESULT
Particle Shedding (Helmke Drum Test)	≥ 0.5Qm (counts/min) <2000

### ASTM F739-12 TEST METHOD RESULTS

DRUG	Mean Breakthrough Time (MBT), Minutes Breakthrough of the test chemical is deemed to have occurred when the permeation rate has reached 0.1 Qg/cm <sup>2</sup> /min
CISPLATIN	>240
CARMUSTINE	<6
CYCLOPHOSAMIDE	217 (275,162,215)
DOXORUBICINHYDROCHLORIDE	>240
5-FLUOROURACIL	>240
METHOTREXATE	>240
ETOPOSIDE	>240
PACLITAXEL	<10
THIOTEPA	30 (28,30,33)

Results achieved under controlled laboratory conditions, by accredited external testing laboratory. \*For Bioclean D and Bioclean 2000, the chemical permeation results relates to the fabric performance for reference only. Seams and closures may have lower breakthrough times. We recommend garments with sealed seams such as Bioclean-C to be worn over the coverall for added protection against chemotherapy drugs handling.

### SIZE CHART

Universal



# BioClean-D™ Hood BDHD-L

## MATERIAL PERFORMANCE TEST RESULTS

TEST	RESULT	PERFORMANCE CLASS	PERFORMANCE STANDARD
Abrasion Resistance	>10 cycles	1	EN 12947-2
Flex Cracking Resistance	>50,000 cycles	6	EN ISO 7854
Puncture Resistance	>5 N	1	ISO 13996
Trapezoidal Tear Resistance Cross Direction (CD)	>10 N	1	EN ISO 9073-4
Trapezoidal Tear Resistance Machine Direction (MD)	>10 N	1	EN ISO 9073-4
Tensile Strength Cross Direction (CD)	>30 N	1	EN ISO 13934-1
Tensile Strength Machine Direction (MD)	>30 N	1	EN ISO 13934-1
Repellence to Liquids - 30% H <sub>2</sub> SO <sub>4</sub>	>90%	3	ISO 6530
Repellence to Liquids - 10% NaOH	>90%	3	ISO 6530
Repellence to Liquids - O-Xylene	>90%	3	ISO 6530
Repellence to Liquids - Butan-1-ol	>90%	3	ISO 6530
Penetration by Liquids - 30% H <sub>2</sub> SO <sub>4</sub>	<1%	3	ISO 6530
Penetration by Liquids - 10% NaOH	<1%	3	ISO 6530
Penetration by Liquids - O-Xylene	<1%	3	ISO 6530
Penetration by Liquids - Butan-1-ol	<1%	3	ISO 6530
Seam Strength <sup>2</sup>	>50 N	2	ISO 13935-2
Electrostatic Charge Half Decay Time, t <sub>50</sub> (secs)	PASS	N/A	EN1149-3

1. Seam not destroyed
2. The material is static dissipative. Tested in accordance with EN1149-5

## ORDERING INFORMATION

	SIZE	Universal
BDHD-L	REORDER NO.	BDHD-L

### Performance Standards and Regulatory Compliance



CE 0598



For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at

#### Europe, Middle East & Africa Region

Ansell Healthcare Europe NV  
T: +32 (0) 2 528 74 00  
F: +32 (0) 2 528 74 01

#### Asia Pacific Region

Ansell Global Trading Center  
T: +603 8310 6688  
F: +603 8310 6699

#### North America Region

Ansell Healthcare Products LLC  
US T: +1 800 800 0444  
US F: +1 800 800 0445  
CA T: +1-800-363-8340

#### Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.  
T: +52 442 248 1544 / 248 3133

#### Australia

Ansell Limited  
T: +61 1800 337 041  
F: +61 1800 803 578

#### UK

Ansell Nitritex  
T: +44 1638 663338  
F: +44 1638 668890



TYPE PB [6]

Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: [www.ansell.com/patentmarking](http://www.ansell.com/patentmarking) © 2024 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

Please see product validation pack or contact Ansell customer service for specific data on use of garments with cytotoxic drugs. Garments used for protection against such drugs must be selected specifically for the type of chemicals used.

