


Sterile, nonwoven polycellulose wipes, providing superior absorption capabilities

- **Enhanced absorbency:** BioClean™ Oryx BOWS cleanroom wipes are composed of hydroentangled polycellulose, delivering outstanding absorption properties
- **Minimized allergy risks:** They feature no whitening agents or optical brighteners, reducing the risk of allergic reactions
- **Guaranteed cleanliness:** These low-linting wipes are sterilized via gamma irradiation and packed in an ISO Class 5 cleanroom facility, ensuring low levels of particulates and extractables, while sampling and inspection are carried out in accordance with ISO 2859-3 standards
- **Heightened robustness:** BioClean™ Oryx BOWS nonwoven wipes also benefit from excellent durability and strength



Key Features and Benefits

- **Hydroentangled polycellulose design:** Excellent absorption properties
- **No optical brighteners or whitening agents:** Lesser allergy risks
- **ISO Class 5 cleanroom-packed:** Minimal extractable and particulate levels

Industries

- Controlled and Critical Environments
- Production and Manufacturing



BioClean™ Oryx BOWS 9B

TECHNICAL DATA SHEET

PRODUCT INFORMATION

| | |
|--------------------------------|--|
| Material | Polycellulose |
| Color | White |
| Audit Standards | ISO 9001 |
| Standards | ISO 2859, ISO 9001:2015 |
| Packaging Overview | BOWS-9B: 300 pieces (flat) per sealed inner PE bag; one inner PE bags per sealed outer PE bag; eight outer bags per lined carton (2400 pieces) |
| Country Of Origin | China |
| Available Sizes | 230mm x 230mm (9" x 9") |
| Sterilization Method | GAMMA irradiation (25 kGy) |
| Cut | Blade |
| Weight | 68gsm (±3gsm) |
| Cleanroom Class | Class 100/ISO Class 5 & EU GMP Grade A/B and other sterile cleanrooms |
| Shelf Life | Five (5) years from date of manufacture. |
| Test Reports Available on File | Test, test 1 |

PHYSICAL PROPERTIES

| | | |
|--------------------|--|--------|
| Force at Break (N) | Machine Direction | 98 |
| | Cross Direction | 42 |
| Absorption | Extrinsic Sorbency Capacity (ml/m ²) | 305.90 |
| | Intrinsic Sorbency Capacity (ml/g) | 4.60 |

| Typical Extractable Ions | | | | | |
|--------------------------|--------|-----------|-----------|---------|----------|
| | Sodium | Potassium | Magnesium | Calcium | Chloride |
| (µg/cm ²) | 0.422 | 0.038 | 0.116 | 0.228 | 0.07 |

ND = Not Detected, NT = Not Tested

| | | | |
|--|--|--------------------|------------------|
| Particle generation (≥0.5µm) orbital shake method | 4.6 x 10 ³ /cm ² | | |
| Particle generation Helmke drum method (average counts per minute) | ≥0.3µm | ≥0.5µm | ≥5.0µm |
| | 1261 DRY / 363 WET* | 850 DRY / 170 WET* | 85 DRY / 29 WET* |

ORDERING INFORMATION

| | | |
|---------|-------------|-------------------------|
| | SIZE | 230mm x 230mm (9" x 9") |
| BOWS 9B | REORDER NO. | BOWS-9B |

For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV
T: +32 (0) 2 528 74 00
F: +32 (0) 2 528 74 01

Asia Pacific Region

Ansell Global Trading Center
T: +603 8310 6688
F: +603 8310 6699

North America Region

Ansell Healthcare Products LLC
US T: +1 800 800 0444
US F: +1 800 800 0445
CA T: +1-800-363-8340

Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.
T: +52 442 248 1544 / 248 3133

Australia

Ansell Limited
T: +61 1800 337 041
F: +61 1800 803 578

UK

Ansell Nitritex
T: +44 1638 663338
F: +44 1638 668890

Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending; www.ansell.com/patentmarking © 2025 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

