

## Latex exam gloves with exceptional fit and feel for extended wear

- **Secure grip:** MICROFLEX™ Diamond Grip Plus™ DGP-350 latex medical exam gloves are fully textured, for a secure grip in both wet or dry environments
- **Tactile sensitivity:** Excellent tactile sensitivity ensures precise handling during patient care or when handling delicate products or laboratory instruments
- **Comfortable and elastic fit:** Superior elasticity means gloves move with you for greater comfort
- **Outstanding quality:** Exceeds standards for tensile strength, elasticity/elongation and other quality standards for average latex gloves



**\*CAUTION:** This product contains natural rubber latex, which may cause allergic reactions

### Industries

- Food Processing
- Life Sciences
- Dental
- Healthcare
- Infrastructure Maintenance
- Automotive Aftermarket

### Recommended For

- All food processing, applications that have food contact
- Sample taking and processing
- Equipment repair and maintenance
- Extra comfort during long, sustained procedures
- Standard patient examinations

# TECHNICAL DATA SHEET

Product Information	
<b>Material</b>	Natural Rubber Latex
<b>External Glove Surface</b>	Fully Textured
<b>Audit Standards</b>	EN ISO 13485:2012
<b>Product Certification</b>	ASTM D3578, EN ISO 21420:2020, FDA21 CFR 177-2600-US Food Contact Approved, US QSR/FDA 510(k) Medical Examination Grade
<b>Packaging Overview</b>	100 gloves per dispenser 10 dispensers per case 1000 gloves per case
<b>Storage Instructions</b>	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.
<b>Country Of Origin</b>	Malaysia
<b>Antistatic</b>	Not Tested
<b>Silicone Free</b>	Yes

## PHYSICAL PROPERTIES

	Typical Values		Testing Method
Length (mm/inches)	245 / 9.65		ASTM D3767,EN 420
Freedom from Holes (Inspection level I)	1.5 AQL		ASTM D5151,EN 455-1
Palm Thickness (mm/mils)	0.14 / 5.51		ASTM D3767,EN 420
Finger Thickness (mm/mils)	0.17 / 6.69		ASTM D3767,EN 420
	<b>BEFORE AGING</b>	<b>AFTER AGING</b>	
Ultimate Tensile Strength (MPa)	18	14	ASTM D412 & D573
Elongation at Break (%)	≥ 700	≥ 600	ASTM D412
Force at break (N)	9	9	EN 455-2

## ORDERING INFORMATION

Size	XS (5.5 - 6)	S (6.5 - 7)	M (7.5 - 8)	L (8.5 - 9)	XL (9.5 - 10)
Product Code	DGP-350-XS	DGP-350-S	DGP-350-M	DGP-350-L	DGP-350-XL

**For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at**

**Europe, Middle East & Africa Region**

Ansell Healthcare Europe NV

T: +32 (0) 2 528 74 00  
F: +32 (0) 2 528 74 01

**Asia Pacific Region**

MY: +603 8310 6688  
apac.medical@ansell.com  
CN: +86 21 38275000  
infochina@ansell.com  
JP: +813 5549 8151  
info.medical.jp@ansell.com

**North America Region**

Ansell Healthcare Products LLC

T: +1 800 800 0444  
F: +1 800 800 0445

**Latin America & Caribbean Region**

BR: +55 (11) 3356-3100  
latam.medical@ansell.com  
MX: +52 442 296 2050  
latam.medical@ansell.com  
CO: +57 1 288 3247  
latam.medical@ansell.com

**Australia**

Ansell Limited

T: +61 1800 337 041  
F: +61 1800 803 578

**Russia**

Ansell PYC  
Ten. +7 495 258 13 16

Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending; [www.ansell.com/patentmarking](http://www.ansell.com/patentmarking) © 2025 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

